



Specifications T&M 1000

Construction Structuur	Tufted 1/10" Frisé Getuft 1/10" Frisé	Pile density Pooldichtheid	Ca. 0,161g/m2	Size Afmetingen	2 m wide
Pile material Poolmateriaal	Polyamide 6,6, HS Frisé	Tuft density Aantal punten	Ca. 232.600 /m2	Number of Colours Aantal Kleuren	Unlimited
Primarybacking Draagdoek	Polyester nonwoven	Classification Classificatie	EN1307 23/33-LC3	Soundabsorption Geluidsabsorptie	ISO 354 < 2,0 kV
Secondary backing Rugafwerking	Actionback	Fire resistance Brandgedrag	EN 13501-1 bfl-s1	Impact noise Geluids isolatie	ISO 140-8 27 dB β
Total weight Totaal gewicht	Ca. 2100 g/m2	Fastnes to light Lichtechtheid	EN ISO 105-BO2 > 5	Thermal ressoratance Warmte-doorlaatweerstand	ISO 8302 0,074 m2 K/W
Pile weight Poolgewicht	Ca. 1000 g/m2	Rubbing fastness Wrijfechtheid	EN ISO 105-X12 > 5	Colour fastness to water Waterrechtheid	Oekotex ® 100 Change in colour: 4-5 Staining: 4
Pile above backing Nuttig poolgewicht	Ca. 727 g/m2	Pile height Poolhoogte	Ca. 6 mm	Total height Totale dikte	Ca. 8 mm
Castorchairsuitability Rolstoegeschiktheid	EN 985 Intensive use	Permanent antistatic Permanent antistatisch	ISO 6356 < 2,0 kV	Transversal resistance Doorgangs weerstand	ISO 10965 < 10. Ohm



T&M Nederland B.V.
www.textilesandmore.eu
info@textilesandmore.eu
+31(0)88 -166 90 00





Specifications T&M 1004

Construction Structuur	Tufted 1/10" Saxony Getuft 1/10" Saxony	Pile density Pooldichtheid	-	Size Afmetingen	400 / 200 cm wide
Pile material Poolmateriaal	Polyamide 6	Tuft density Aantal punten	Ca. 240.000 /m2	Number of Colours Aantal Kleuren	Unlimited
Primarybacking Draagdoek	Polyester nonwoven	Classification Classificatie	33	Soundabsorption Geluidsabsorptie	EN ISO 10140 29 dB
Secondary backing Rugafwerking	Actionback	Fire resistance Brandgedrag	EN 13501-1 cfl-s1	Impact noise Geluids isolatie	ISO 10140 29 dB
Total weight Totaal gewicht	Ca. 1750 g/m2	Fastnes to light Lichtechtheid	EN ISO 105-BO2 > 5	Thermal resistance Warmte doorlaatweerstand	ISO 8302 Ca. 0,08 m K/W
Pile weight Poolgewicht	Ca. 1000 g/m2	Rubbing fastness Wrijftechtheid	EN ISO 105-X12 > 4	Colour fastness to water Waterrechtheid	Oekotex [®] 100 Change in colour: 4-5 Staining: 4
Pile above backing Nuttig poolgewicht	Ca. 900 g/m2	Pile height Poolhoogte	Ca. 6 mm	Total height Totale dikte	Ca. 7 mm
				Permanent antistatic Permanent antistatisch	ISO / DIS 10965 10 OHM



T&M Nederland B.V.
www.textilesandmore.eu
info@textilesandmore.eu
+31(0)88 -166 90 00

